414 Rec'd PCT/PTO 26 DEC 2000

FORM PTO-1390 (Modified) (REV 11-98) U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371

ATTORNEY'S DOCKET NUMBER	U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR
NAK1-BN46	09/720609

INTERNATIONAL APPLICATION NO.	INTERNATIONAL FILING DATE	PRIORITY DATE CLAIMED
PCT/JP00/02715	April 26, 2000	April 28, 1999

TITLE OF INVENTION

PLASMA DISPLAY PANEL MANUFACTURING METHOD FOR ACHIEVING LUMINESCENCE CHARACTERISTICS

APPLICANT(S) FOR DO/EO/US

Masaki Aoki o et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☐ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
   a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
   b. ☒ has been transmitted by the International Bureau.
   c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
   a. ☒ are transmitted herewith (required only if not transmitted by the International Bureau).
   b. ☐ have been transmitted by the International Bureau.
   c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
   d. ☐ have not been made and will not be made.
9. ☒ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 20 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☒ Certificate of Mailing by Express Mail
20. ☒ Other items or information:

Copy of PCT Request
Copy of PCT Publication

526 Rec'd PCT/PTO 26 DEC 2000

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR)	INTERNATIONAL APPLICATION NO.	ATTORNEY'S DOCKET NUMBER
09/720609	PCT/JP00/02715	NAK1-BN46

21. The following fees are submitted:.

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

		CALCULATIONS PTO USE ONLY
☐	Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2) paid to USPTO and International Search Report not prepared by the EPO or JPO $1,000.00	
☒	International preliminary examination fee (37 CFR 1.482) not paid to USPTO but Internation Search Report prepared by the EPO or JPO $860.00	
☐	International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO $710.00	
☐	International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) $690.00	
☐	International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) $100.00	
	ENTER APPROPRIATE BASIC FEE AMOUNT =	$860.00
	Surcharge of **$130.00** for furnishing the oath or declaration later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (e)).	$0.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	19 - 20 =	0	x $18.00	$0.00	
Independent claims	8 - 3 =	5	x $80.00	$400.00	
Multiple Dependent Claims **(check if applicable)**.			☐	$0.00	
	TOTAL OF ABOVE CALCULATIONS =			$1,260.00	
	Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) **(check if applicable).** ☐			$0.00	
	SUBTOTAL =			$1,260.00	
	Processing fee of **$130.00** for furnishing the English translation later than ☐ 20 ☐ 30 months from the earliest claimed priority date (37 CFR 1.492 (f)). +			$0.00	
	TOTAL NATIONAL FEE =			$1,260.00	
	Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) **(check if applicable).** ☒			$40.00	
	TOTAL FEES ENCLOSED =			$1,300.00	
				Amount to be: refunded	$
				charged	$

☒ A check in the amount of **$1,300.00** to cover the above fees is enclosed.

☐ Please charge my Deposit Account No. in the amount of to cover the above fees.
A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **16-2462** A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Joseph W. Price, Reg. No. 25,124
PRICE AND GESS
2100 S.E. Main St., Ste. 250
Irvine, CA 92614
Tel: 949/261-8433
Fax: 949/261-9071

SIGNATURE

Joseph W. Price
NAME

25,124
REGISTRATION NUMBER

December 26, 2000
DATE

09/720609
526 Rec'd PCT/PTO 26 DEC 2000

NAK1-BN46

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:	Examiner:
Masaki AOKI et al.	Group Art Unit:
Serial No.:	
Filed:	Irvine, CA 92614
For: PLASMA DISPLAY PANEL AND METHOD FOR PRODUCING THE PLASMA DISPLAY PANEL	December 26, 2000

09/720609 12/26/00

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Dear Sir:

Prior to an examination on the merits of the above-identified application, please enter the following amendments:

IN THE CLAIMS:

Please cancel Claims 1, 11, 12, 13, 14, 15, 16, and 17 without prejudice.

Please amend the claims as follows:

Claim 2, line 1, delete "1" and insert --20--;

Claim 3, line 1, delete "1" and insert --20--;

Claim 4, line 1, delete "1" and insert --20--;

Claim 5, line 1, delete "1" and insert --20--;

Claim 6, line 1, delete "1" and insert --20--;

Claim 7, line 1, delete "1" and insert --20--;

Claim 8, line 1, delete "1" and insert --20--;

Claim 9, line 1, delete "1" and insert --20--;

Claim 10, line 1, delete "1" and insert --20--;

Claim 18, line 1, delete "17" and insert --27--;

Claim 19, line 1, delete "17" and insert --27--.

Please add the following newly-drafted Claims 20-27.

20. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass that contains at least ZnO and 10 wt% or less of R_2O and does not substantially contain PbO and Bi_2O_3, and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag.

21. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 20-30 wt% of P_2O_5, 30-40 wt% of ZnO, 30-45 wt% of B_2O_3, and 1-10 wt% of SiO_2 and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less.

22. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass. which is composed of 30-45 wt% of ZnO, 40-60 wt% of B_2O_3, and 1-15 wt% of SiO_2 and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less.

23. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 30-45 wt% of ZnO, 40-55 wt% of B_2O_3, 1-10 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 1-5 wt% of CaO, and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less.

24. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first

plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which. is composed of 40-60 wt% of ZnO, 35-45 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of $A1_2O_3$, and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less.

25. (Amended) A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 30-60 wt% of ZnO, 30-50 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of $A1_2O_3$, and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less.

26. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 9-20 wt% of Nb_2O_5, 35-60 wt% of ZnO, 25-40 wt% of B_2O_3, and 1-10 wt% of SiO_2, and a product of permittivity ε and loss factor tan δ of the dielectric layer is 0.12 or less.

27. A plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is composed of

a first dielectric layer which either is a thin film of SiO_2, $A1_2O_3$ or ZnO or is made of a glass containing at least PbO or Bi_2O_3 and covers the plurality of pairs of display electrodes, and

a second dielectric layer made of a glass in which a product of permittivity ε and loss factor tan δ is 0.12 or less, the second dielectric layer covering the first dielectric layer.

REMARKS

The newly drafted Claims 20-27 are within the scope of the original invention and do not add any new subject matter.

If the Examiner believes that a telephone interview will help further the prosecution of this case, he is respectfully requested to contact the undersigned attorney at the listed telephone number.

Very truly yours,

PRICE AND GESS



Joseph W. Price, Reg. 251,24
2100 S.E. Main St., Ste. 250
Irvine, CA 92614
949/261-8433

DRAFT - PENDING

3/PRTS
09/720609
526 Rec'd PCT/PTO 26 DEC 2000

DESCRIPTION

PLASMA DISPLAY PANEL AND METHOD FOR PRODUCING THE PLASMA DISPLAY PANEL

TECHNICAL FIELD

The present invention relates to a plasma display panel used for a display device or the like. More particularly, the present invention relates to a dielectric layer.

BACKGROUND ART

Recently, high performance displays such as high-definition (e.g., Hi-Vision) or large-scale displays are much sought after, and various studies are performed for developing high-performance displays such as CRT displays, liquid crystal displays (LCD), and plasma display panel (PDP).

PDP is a kind of gas-discharge panel. To manufacture a PDP, two thin glass plates are disposed to face each other with partition walls (ribs) in between, and a plurality of pairs of display electrodes, a dielectric layer (typically, made of Ag or Cr/Cu/Cr in order to secure good conductivity), and a phosphor layer are formed in this order on the surface of one of the two thin glass plates facing the ribs, then the space between the two thin glass plates is filled with a discharge gas, and the space is sealed hermetically. Discharges are

caused in the discharge gas to allow the phosphor to emit light. PDP has excellent characteristics. That is to say, unlike CRT, a large-screen PDP is not remarkably deep and heavy. Also, PDP does not have the problem of limited viewing angle which is observed in LCD.

Typically, the dielectric layer is made of a low-melting glass. In this case, characteristics such as enough dielectric strength, high transparency, and low baking temperature (more specifically, 600℃ or lower) are required. Glasses actually used for dielectric glass layers are lead oxide (PbO), glass (permittivity ε = 10-15) including bismuth oxide (Bi_2O_3), etc. (See Japanese Laid-Open Patent Application No.9-50769, for example).

Meanwhile, as it is desired in these days that the power consumption of electrical appliances is as small as possible, it is expected that the driving power consumption will be further reduced. Especially, considering that the power consumption of PDP is increasing due to the demand for larger-screen and higher-definition displays, it is required that the power consumption is reduced more aggressively.

One method of reducing the power consumption is to reduce the permittivity ε in the dielectric layer. The permittivity ε in the dielectric layer is proportionate to the amount of electric charge accumulated in the dielectric layer. It is therefore possible to further reduce the amount of

electric charge accumulated in the dielectric layer by using a dielectric layer having composition with a permittivity ε value lower than the PbO-base or Bi_2O_3-base dielectric layer. Japanese Laid-Open Patent Application No.8-77930 discloses specific glass composition with a permittivity ε value lower than the PbO-base or Bi_2O_3-base dielectric layer: Na_2O-B_2O_3-SiO_2-base glass and Na_2O-B_2O_3-ZnO-base glass both with a permittivity ε value of 7.2-7.6. It is possible to reduce amount of discharge current in each pixel cell per a certain voltage applied to the plurality of pairs of display electrodes (to about half or less of conventional ones) by using glasses with the above composition. This reduces the power consumption of the PDP. Also, according to the document, the dielectric layer can be formed without using a PbO-base glass. This provides an effect of avoiding environmental pollution with Pb.

It should be noted that in actual manufacturing of a PDP using the Na_2O-B O -SiO -base glass or Na O-B O -ZnO-base glass, Na_2O is added to constitute more than 10 wt% of the whole dielectric layer to reduce the softening point (more specifically, to set the baking temperature to a range of 550℃ to 600℃).

However, when the dielectric layer is made of the Na_2O-B_2O_3-SiO_2-base glass or Na_2O-B_2O_3-ZnO-base glass, Ag and Cu contained in the display electrodes move into the dielectric layer and are deposited as colloidal particles (see Latest

Plasma Display Manufacturing Technique, 1987 edition, page 234). The colloidal particles reflect visible light of a certain wavelength. This turns the color of the dielectric layer to yellow (what is called yellowing). This puts an undesired color to the light emitted from the discharge space, or reduces the amount of light to be obtained. As apparent from the above, the colloidal particles can be a cause of ill effects on display performance. When Na_2O is added to constitute more than 10 wt% of the whole dielectric layer, this could also be a cause of the yellowing. For these reasons, the deposition of the colloidal particles should be avoided.

The addition of Na_2O to constitute more than 10 wt% of the whole dielectric layer provides another ill effect of increasing $\tan\delta$ which indicates power loss in the dielectric layer. More specifically, it decreases the dielectric strength of the dielectric layer (having thickness of 20-50μm) to approximately 1 kV.

As described above, plasma display panels have the following three main problems currently:

*1. To improve luminous efficiency by reducing the permittivity ε of the dielectric layer to reduce power consumption;

*2. To set the softening point of the dielectric layer to a low value to ease the manufacturing process; and

*3. To obtain superior display performance by preventing the yellowing of the dielectric layer to securing its

transparency.

The present invention is provided to solve the above three problems and an object of the present invention to provide a PDP characterized in that the dielectric layer can be formed relatively easily, that the increase in the power consumption is restricted even if the PDP has a larger screen or higher definition, and that the PDP is driven with better luminous efficiency and display performance than conventional ones.

DISCLOSURE OF INVENTION

The inventors of the present invention studied hard to solve the above problems and provide a plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag or Cu are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that: the dielectric layer is made of a glass that contains at least ZnO and 10 wt% or less of R_2O and does not substantially contain PbO and Bi_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag.

The inventors of the present invention have found that

with the above construction, the amount of R_2O in the dielectric layer is reduced, the deposition of the colloidal particles is suppressed, excellent transparency of the dielectric layer is secured, and the power consumption is reduced compared with conventional ones. The inventors have also found that the dielectrics layer can be baked at 600℃ or lower. As understood from this, the present invention can reduce the manufacturing cost (e.g., the cost for baking the dielectrics layer) and drive the plasma display panel with excellent display performance and luminous efficiency and with less power than conventional ones. Also, since the above glass composition does not contain Pb, environmental pollution with Pb can be avoided.

It should be noted here that the numerical definition "0.12 or less" for the product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is required to reduce power consumption, and this specific value range was determined from the data of Examples which will be described later.

In the above plasma display panel, it is desirable that the permittivity ε of the dielectric layer is 7 or less since it will effectively reduce the value $\varepsilon \cdot \tan\delta$.

With regard to specific glass composition of the dielectric layer, it has been found from data of Examples which will be described later that the following glass compositions are desirable.

The dielectric layer may contain 10-25 wt% of P_2O_5,

20-35 wt% of ZnO, 30-40 wt% of B_2O_3, 5-12 wt% of SiO, 10 wt% or less of R_2O, and 10 wt% or less of DO, and the permittivity ε of the dielectric layer is 7 or less, wherein D is selected from a group consisting of Mg, Ca, Ba, Sr, Co, Cr, and Ni.

The dielectric layer may be composed of a ZnO-P_2O_5-base glass which contains 42-50 wt% of P_2O_5, 35-50 wt% of ZnO, 7-14 wt% of Al_2O_3, and 5 wt% or less of Na O, and the permittivity ε of the dielectric layer is 7 or less.

The dielectric layer may be composed of a ZnO-base glass which contains 20-44 wt% of ZnO, 38-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 10 wt% or less of R_2O, and 10 wt% or less of MO, and the permittivity ε of the dielectric layer is 7 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag, and M is selected from a group consisting of Mg, Ca, Ba, Sr, Co, and Cr.

The dielectric layer may be composed of a ZnO-base glass which contains 20-43 wt% of ZnO, 38-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 1-10 wt% of Al_2O_3, 10 wt% or less of R_2O, and 10 wt% or less of MO, and the permittivity ε of the dielectric layer is 7 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag, and M is selected from a group consisting of Mg, Ca, Ba, Sr, Co, and Cr.

The dielectric layer may be composed of a ZnO-base glass which contains 1-15 wt% of ZnO, 20-40 wt% of B_2O_3, 10-30 wt% of SiO_2, 5-25 wt% of Al_2O_3, 3-10 wt% of Li_2O, and 2-15 wt%

of MO, and the permittivity ε of the dielectric layer is 7 or less, wherein M is selected from a group consisting of Mg, Ca, Ba, Sr, Co, and Cr.

The dielectric layer may be composed of a ZnO-base glass which contains 35-60 wt% of ZnO, 25-45 wt% of B_2O , 1-10.5 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 5 wt% or less of Na_2O, and the permittivity ε of the dielectric layer is 7 or less.

The dielectric layer may be composed of a ZnO-base glass which contains 35-60 wt% of ZnO, 25-45 wt% of B_2O_3, 1-12 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 5 wt% or less of K_2O, and the permittivity ε of the dielectric layer is 7 or less.

The dielectric layer may be composed of a ZnO-Nb_2O_5-base glass which contains 9-19 wt% of Nb_2O_5, 35-60 wt% of ZnO, 20-38 wt% of B_2O_3, 1-10.5 wt% of SiO_2, and 5 wt% or less of Li_2O, and the permittivity ε of the dielectric layer is 7 or less.

With regard to specific glass composition of the dielectric layer, it has been found from data of Examples which will be described later that the following glass compositions dispense with R_2O.

The dielectric layer may be made of a glass which is composed of 20-30 wt% of P_2O_5, 30-40 wt% of ZnO, 30-45 wt% of B_2O_3, and 1-10 wt% of SiO_2 and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

The dielectric layer may be made of a glass which is composed of 30-45 wt% of ZnO, 40-60 wt% of B_2O_3, and 1-15 wt% of

SiO_2 and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

The dielectric layer may be made of a glass which is composed of 30-45 wt% of ZnO, 40-55 wt% of B_2O_3, 1-10 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 1-5 wt% of CaO, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

The dielectric layer may be made of a glass which is composed of 40-60 wt% of ZnO, 35-45 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of Al_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

The dielectric layer may be made of a glass which is composed of 30-60 wt% of ZnO, 30-50 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of Al_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

The dielectric layer may be made of a glass which is composed of 9-20 wt% of Nb_2O_5, 35-60 wt% of ZnO, 25-40 wt% of B_2O_3, and 1-10 wt% of SiO_2, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

The above object is also fulfilled by a plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag or Cu are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer

covering the plurality of pairs of display electrodes, characterized in that: the dielectric layer is composed of a first dielectric layer which either is a thin film of SiO_2, Al_2O_3, or ZnO or is made of a glass containing at least PbO or Bi_2O_3, and covers the plurality of pairs of display electrodes, and a second dielectric layer made of a glass in which a product of permittivity ε and loss factor $\tan\delta$ is 0.12 or less, the second dielectric layer covering the first dielectric layer.

With the above construction, the first dielectric layer effectively suppresses colloidal particles from being deposed out of the plurality of pairs of display electrodes, secures excellent transparency of the dielectric layer, and enhances the display performance of the plasma display panel. The second dielectric layer effectively reduces the power consumption of plasma display panel by reducing the permittivity ε value.

A total thickness of the dielectric layer may be 40 μm or less, and a thickness of the first dielectric layer may be half of the total thickness or less. With this construction, it is possible to reduce the total amount of Pb used for the dielectrics layer, providing an effect of avoiding environmental pollution with Pb. It should be noted here that the value "40 μm" indicates the maximum thickness of general dielectric layers.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a perspective, sectional view showing main components of the AC surface-discharge type PDP in Embodiment 1.

FIG. 2 is a partial sectional view of the PDP showing a detailed construction of the dielectric layer in Embodiment 2 and the surroundings.

FIG. 3 is a partial sectional view of the PDP showing a detailed construction of a conventional dielectric layer and the surroundings.

BEST MODE FOR CARRYING OUT THE INVENTION

1. Embodiment 1

1-1. Entire Construction of PDP

FIG. 1 is a perspective, sectional view showing main components of the AC surface-discharge type plasma display panel (hereinafter called PDP) in Embodiment 1. In the drawing, the z direction is a direction along thickness of the PDP and the xy plane is parallel to the panel surface of the PDP. Though the size of the PDP in the present embodiment conforms to the VGA specifications for 42-inch class, the present invention can be applied to other sizes as well.

As shown in FIG. 1, the PDP is roughly divided into the front panel 20 and the back panel 26 which are disposed so that their main surfaces face each other.

On one surface of the front panel glass 21, which is the substrate of the front panel 20, a plurality of pairs of display electrodes 22 and 23 (an X electrode 23 and a Y electrode 22) are disposed in the x direction, where the y direction is the direction of the length, and each pair of display electrodes 22 and 23 are composed of 0.1μm-thick, 370μm-wide belt-shaped transparent electrodes 220 and 230 and 5μm-thick, 100μm-wide bus lines 221 and 231. A surface discharge is performed in a space (approximately 80 μm) between each pair of display electrodes 22 and 23. The bus lines 221 and 231 are made of Ag or Cr/Cu/Cr having superior conductivity.

It should be noted that the above plurality of pairs of display electrodes 22 and 23 may be composed of only bus lines. In this case, it is desirable that the space between each pair of display electrodes 22 and 23 is approximately 80 μm.

The main surface of the front panel glass 21 with the display electrodes 22 and 23 having been disposed on it is coated with an approximately 30μm-thick dielectric layer 24 (its detailed composition will be described later) first, and with an approximately 1.0μm-thick protection layer 25 made of magnesium oxide (MgO).

On one surface of the back panel glass 27, which is the substrate of the back panel 26, a plurality of 5μm-thick,

100 μm-wide address electrodes 28 are disposed in stripes at regular intervals (at intervals of approximately 150 μm) in the y direction, where the x direction is the direction of the length. The main surface of the back panel glass 27 with the address electrodes 28 having been disposed on it is coated with a 30 μm-thick dielectric film 29.

On the surface of the dielectric film 29, approximately 150 μm-high, approximately 40 μm-wide ribs 30 are disposed to match spaces between the plurality of address electrodes 28. In each channel composed of two sides of two adjacent ribs 30 and the surface of the dielectric layer 29, one of phosphor layers 31 to 33 corresponding to red (R), green (G), and blue (B) is formed. The phosphor layers 31 to 33 of red, green, and blue are repeatedly disposed in sequence in the x direction.

The front panel 20 and the back panel 26 with the above construction are disposed so that the length of the address electrodes 28 is perpendicular to the length of the display electrodes 22 and 23. The outer regions of the panels 20 and 26 are bonded to be sealed. A discharge gas (seal-in gas) composed of a rare gas such as He, Xe, or Ne is sealed in the space between the panels 20 and 26 with a certain pressure (in the typical, conventional cases, with a pressure of approximately 500-760 Torr).

Each space between two adjacent ribs 30 is a discharge

space 38. Each area at the intersection of a pair of adjacent display electrodes 22 and an address electrode 28 with a discharge space 38 in between corresponds to a cell (not illustrated) used for displaying images. The cell pitch in the x direction is approximately 1080 μm and the cell pitch in the y direction is approximately 360 μm.

When the PDP is driven, a panel driving unit (not-illustrated) applies a pulse to the address electrode 28 and one of the display electrodes 22 and 23 to generate a writing discharge (address discharge) in each cell. Note that in Embodiment 1, the panel driving unit applies a pulse to the X electrode 23. Generally, the X electrode 23 is called a scan electrode, and the Y electrode 22 a sustain electrode. The panel driving unit then applies a pulse to between a pair of display electrodes 22 and 23 to generate a discharge, which generates ultraviolet rays of short wavelength (resonance lines with central wavelength of 147 nm). This allows the phosphor layers 31-33 to emit light and display an image.

The main characteristic of the present PDP is in the composition of the dielectric layer 24. That is to say, the dielectric layer 24 is composed of a ZnO-P_2O_5-base glass (hereinafter called ZnO-P_2O_5-base glass of the present invention) that does not include PbO or Bi_2O_3. The ZnO-P_2O_5-base glass of the present invention is composed of, for example, 10 wt% of P_2O_5, 20 wt% of ZnO, 40 wt% of B_2O_3, 12 wt% of SiO_2, 3 wt%

of BaO, and 10 wt% of Na_2O. The $ZnO-P_2O_5$-base glass of the present invention has a lower permittivity ε value than PbO-base glasses or Bi_2O_3-base glasses that have conventionally been used for the dielectric layer (more specifically, while the permittivity ε value of PbO-base or ZnO-base glasses is approximately 10 to 12, that of the present invention is approximately 7 or lower). Also, the conventional product of the permittivity ε value and the loss factor, $\varepsilon \cdot \tan\delta$ is 0.14-0.7. The $\varepsilon \cdot \tan\delta$ value of the dielectric layer 24 in Embodiment 1 is approximately 0.103 or lower, which is much lower than the conventional one.

1-2. Effects of Construction of Dielectric Layer in Embodiment 1

FIG. 3 is a partial sectional view of the PDP showing a detailed construction of a conventional dielectric layer and the surroundings. As shown in FIG. 3, in the conventional dielectric layer, Ag and Cu ions contained in the bus lines move into the dielectric layer as colloidal particles, and the colloidal particles reflect visible light, and turn the color of the dielectric layer to yellow (what is called yellowing) (see Latest Plasma Display Manufacturing Technique, 1987 edition, page 234). The yellowing caused by the colloidal particles is remarkable as the amount of R_2O is one of Li, Na, K, Rb, Cs, Cu, and Ag) contained in the glass is much (e.g., more than 10 wt%). In contrast, in the dielectric layer 24 made of the ZnO-

P_2O -base glass of the present invention, the amount of R O (in the present embodiment, $R_2O = Na_2O$) is as small as 10 wt% or less, which suppresses the generation of colloidal particles. As a result, if Ag or Cu are used as the material of the bus lines, the transparency of the dielectric layer 24 is higher than the conventional one. This prevents the above problems of discoloration and light amount loss which occur in the discharge space 38, and provides superior display performance of the PDP.

When a pulse is applied to between a pair of display electrodes 22 and 23 at an early stage of the discharge sustain period for driving the present PDP having the above dielectric layer 24, a discharge is generated there.

In Embodiment 1, the dielectric layer 24 has a lower permittivity ε value (e.g., ε = 6.4) than conventional one (ε = 10-15). As a result, the amount of electric charge accumulated in the dielectric layer 24 before the discharge starts is reduced. This allows the discharge to start with a small amount of current. The present PDP therefore starts discharging with a less power than conventional one, and is driven with less power consumption.

As described above, the PDP of Embodiment 1 has reduced power consumption and superior display performance, and greatly improves the luminous efficiency.

1-3. Relationships between Permittivity ε of Dielectric Layer

and Power Consumption in PDP

Generally, the following formula holds true:

(Formula 1) $C = \varepsilon S/d$,

where S represents the area of a pair of display electrodes 22 and 23, C the capacitance (the capacitance of a portion of the dielectric layer above the discharge space 38) between the pair of display electrodes 22 and 23, d the thickness of the dielectric layer 24, and ε the permittivity ε value of the dielectric layer 24.

Also, the following formula holds true:

(Formula 2) $W = fCV^2 = f(\varepsilon S/d)V^2$,

where V represents the voltage applied to between the pair of display electrodes 22 and 23, f the driving frequency of the panel, and W the power consumption of the PDP.

As apparent from the Formulas 1 and 2, when f and V^2 are constant, the smaller the capacitance C is, the smaller the power consumption W is. Since the capacitance C is proportionate to the permittivity ε, the lower the permittivity ε is, the smaller the power consumption W is (for detailed information, see Transactions of Electrical Engineers of Japan A, Vol. 118, No. 15, 1998, pages 537-542).

Also, when the expression E (electric field strength) = V/d is applied, the following formula holds true (see Electronics Material, Denki Shoin, March 10, 1975, page 23):

(Formula 3) $W \propto f(\varepsilon \cdot \tan\delta)V^2$,

where w represent the power loss of the PDP.

Since generally, the power loss w is proportionate to the power consumption W, it is apparent from the Formula 3 that the lower at least either permittivity ε or $\tan\delta$ value is, the smaller the power consumption W (for detailed information, see Transactions of Electrical Engineers of Japan A, Vol. 118, No. 15, 1998, pages 537-542).

The effect of the PDP in Embodiment 1 can be explained based on the above theory. That is to say, when the dielectric layer 24 is made of the $ZnO-P_2O_5$-base glass of the present invention (that does not contain PbO or Bi_2O_3 but contains P_2O_5, ZnO, B_2O_3, SiO_2, BaO, Na_2O or the like), the product of the permittivity ε value and the loss factor, $\varepsilon \cdot \tan\delta$ is reduced (more specifically, reduced to 0.12 or lower), the power loss w is reduced, and the power consumption W of the PDP is reduced.

The dielectric layer 24 in Embodiment 1 may be made of a ZnO-base glass that does not contain PbO or Bi_2O_3 (hereinafter called a ZnO-base glass of the present invention), which will be described later in another embodiment. The ZnO-base glass of the present invention is composed of, for example, 40 wt% of ZnO, 45 wt% of B_2O_3, 5 wt% of SiO_2, 5 wt% of Al_2O_3, and 5 wt% of Cs_2O. Also, the dielectric layer 24 in Embodiment 1 may be made of a Nb_2O_5-ZnO-base glass that does not contain PbO or Bi_2O_3 (hereinafter called a Nb_2O_5-ZnO-base glass of the present invention). The Nb_2O_5-ZnO-base glass of the present

invention is composed of, for example, 19 wt% of Nb_2O , 44 wt% of ZnO, 30 wt% of B_2O_3, and 7 wt% of SiO_2.

Variations of the composition of the glass used for the dielectric layer 24 will be described in detail in the following embodiments.

2. Embodiment 2

The PDP in Embodiment 2 will be described. The construction of Embodiment 2 is almost the same as Embodiment 1 except for the dielectric layer.

2.1 Construction of Dielectric Layer and Surroundings

FIG. 2 is a partial sectional view of the PDP showing a detailed construction of the dielectric layer 24 in Embodiment 2 and the surroundings. As shown in FIG. 2, the dielectric layer 24 in Embodiment 2 has a two-layered construction in which the second dielectric layer 242 is laid on the first dielectric layer 241.

The first dielectric layer 241 is composed of a 5μm-thick PbO-base glass (which is composed of, in this example, 65 wt% of PbO, 10 wt% of B_2O_3, 24 wt% of SiO_3, 1 wt% of CaO, and 2 wt% of Al_2O_3), and is formed on the main surface of the front panel glass 21 covering the display electrodes 22 and 23.

The second dielectric layer 242 is composed of a 25μm-thick ZnO-P_2O_5-base glass (which is composed of, in this example, 30 wt% of ZnO, 20 wt% of P_2O_5, 40 wt% of B_2O_3, and 10

wt% of SiO_2). The permittivity ε value of the second dielectric layer 242 is approximately 6.3.

2-2. Effects of Dielectric Layer in Embodiment 2

Though the PbO-base glass used for the first dielectric layer 241 has a permittivity ε value (e.g., ε = 11) that is at the same level as the conventional one (ε = 10-15), the PbO-base glass is characterized by suppressing Ag and Cu ions from moving in from the bus lines 221 and 231 as colloidal particles.

In Embodiment 2, the first dielectric layer 241 and the second dielectric layer 242 having the above characteristics are disposed as a stack so that the first dielectric layer 241 made of the PbO-base glass and covering the display electrodes 22 and 23 suppresses the generation of colloidal particles, and the second dielectric layer 242 having a relatively low permittivity ε value reduces the power consumption of the PDP. As another measure for reducing the power consumption of the PDP, the first dielectric layer 241 is formed to be as thin as 5μm to reduce the total permittivity ε value of the dielectric layer 24 so that the amount of electric charge accumulated in the dielectric layer 24 is reduced. Also, by making the first dielectric layer 241 thin as described above, the amount of used Pb is reduced, which is useful in avoiding environmental pollution with Pb.

Generally, the maximum thickness of the dielectric

layer is 40μm. Accordingly, to obtain the effects (e.g., reducing the amount of Pb) of the dielectric layer 24 of the present invention sufficiently, the thickness should be set to 40μm or less. Also, by setting the thickness of the first dielectric layer 241 to half of the total thickness of the dielectric layer 24 or less, the amount of Pb is further effectively reduced.

In the present PDP having the above dielectric layer 24, when a pulse is applied to between each pair of display electrodes 22 and 23 at an early stage of the discharge sustain period for driving the PDP, a discharge is generated in gap between the display electrodes 22 and 23 in the first dielectric layer 241. Plasma of the discharge gas expands to the discharge space 38 via the second dielectric layer 242. The discharge changes to a sustain discharge and the emission luminance gradually increases.

The PDP in Embodiment 2 is driven with a small power consumption since the permittivity ε value of the second dielectric layer 242 is lower than conventional one and as is the case with Embodiment 1, the amount of electric charge accumulated in the dielectric layer and necessary for discharge is reduced.

Also, as is the case with Embodiment 1, the generation of colloidal particles of Ag and Cu contained in the bus lines 221 and 231 is suppressed since the first dielectric layer 241

made of PbO-base glass covers the bus lines 221 and 231. This suppresses the yellowing of the dielectric layer 24 and increases the transparency. As a result, the phosphor light emitted from the discharge space 38 is not discolored and used for the emission display of the PDP in good condition.

The first dielectric layer 241 may be made of a Bi_2O_3-base glass instead of the PbO-base glass, or may be formed as a thin-film oxide layer of SiO_2, Al_2O_3, or ZnO. These thin-film oxide layers can be formed with the sputtering method.

The second dielectric layer 242 may be made of a ZnO-base glass instead of the $ZnO-P_2O_5$-base glass. The specific composition of these glasses will be described in detail in the sections for Examples.

Japanese Laid-Open Patent Application No.9-50769 discloses a two-layered dielectric layer. In this technique, however, the first dielectric layer is made of a ZnO-base glass and the second dielectric layer is made of a PbO-base glass (i.e., the two layers are in reverse order, compared with the dielectric layer of Embodiment 2). The construction disclosed in this document is clearly different from the present invention. In the construction disclosed in this document, Ag and Cu ions tend to move from the bus lines into the first dielectric layer as colloidal particles and cause the yellowing. Furthermore, it is expected that the permittivity ε value of the dielectric layer of this technique is much higher than the

present invention since the ZnO-base glass disclosed in this document contains Bi_2O_3. Judging from these, it is difficult for the technique disclosed in Japanese Laid-Open Patent Application No.9-50769 to obtain the effects of the present invention: small power consumption and suppression of the yellowing of the dielectric layer.

3. PDP Manufacturing Method

The following is a description of an example method of manufacturing the PDPs of the above embodiments.

3-1. Manufacturing Front Panel

An approximately 2.6 mm thick front panel glass 21 made of a soda lime glass is formed with the float method in which the glass material (soda lime glass) is floated on the surface of melted Sn (tin) at approximately 360℃. Display electrodes 22 and 23 are then formed on the surface of the front panel glass 21. To manufacture the display electrodes 22 and 23, first the transparent electrodes 220 and 230 are formed with the following photoetching method.

An approximately 0.5 μm-thick photoresist (e.g., ultraviolet-hardening resin) is applied to the whole surface of the front panel glass 21. A photomask patterning the transparent electrodes 220 and 230 is laid on the applied photoresist, ultraviolet rays are applied to this, and this is soaked in a developing solution to remove unhardened resin. The material (e.g., ITO) for the transparent electrodes 220 and 230

is applied to gaps between the resists on the front panel glass 21. The resists are then removed by a cleaning solution or the like. This completes the transparent electrodes 220 and 230.

Bus lines 221 and 231 each having thickness of approximately 7 μm and width of approximately 50 μm are then formed on the transparent electrodes 220 and 230 using an Ag-base or Cr/Cu/Cr-base metal. In the case of an Ag-base metal, the screen printing method can be used. In the case of a Cr/Cu/Cr-base metal, the vapor deposition or sputtering method can be used.

With the above process, the display electrodes 22 and 23 are formed.

3-1-1. Manufacturing Dielectric Layer in Embodiment 1 (Single-Layered Dielectric Layer)

Here, a method of manufacturing the dielectric layer (using a P_2O_5-ZnO-base glass) in Embodiment 1 will be described.

First, a glass paste is prepared by mixing P_2O_5-ZnO-base glass powder (composed of, for example, 10-25 wt% of P_2O_5, 20-35 wt% of ZnO, 30-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 10 wt% or less of BaO, and 10 wt% or less of Na_2O) with an organic binder solution (a solution mixed with 45 wt% of an organic solvent which contains 0.2 wt% of Homogenol as dispersant, 2.5 wt% of dibutyl phthalate as plasticizer, and 10 wt% of ethyl cellulose) at a ratio of 55:45 by weight. The glass paste is applied, with

the printing method, to the whole surface of the front panel glass 21 on which the display electrodes 22 and 23 have been formed, to form a coat. The coat is baked at temperature of 600℃ or lower (more specifically, for 10 minutes at 520℃) to form the dielectric layer 24 having thickness of 30μm. As described above, the inventors of the present invention have found that with the specific composition of the ZnO-P_2O_5-base glass of the present invention, it is possible to bake the coat at a 600℃ or lower, a temperature relatively low for baking glass, which facilitates the manufacturing process. The material for the dispersant can be selected from the group including Homogenol, sorbitan sesqui-oleate, and polyoxyethylene mono-oleate.

Conventional processes for forming the dielectric layer have a problem that Ag and Cu contained in the bus lines move into the dielectric layer and are deposited as colloidal particles having diameter of 300-400 Å (see FIG. 3). The reason for this is thought to be as follows: when the front panel glass is formed with the float method, Tin ions (Sn^{2+}) are attached to a surface of the front panel glass, remain there and reduce Ag^{+} and Cu^{2+} that have dissolved in the dielectric layer from each bus line (e.g., $2\ Ag^{+} + Sn^{2+} \rightarrow Ag + Sn^{4+}$). Furthermore, when the dielectric layer contains 10 wt% or more of R_2O is one of Li, Na, K, Rb, Cs, Cu, and Ag), the reduction reaction is enhanced. This phenomenon has been revealed by the

inventors of the present invention and others. The reason for this phenomenon is thought to be as follows: Diffusion of Ag^{+} and Cu^{2+} into the dielectric layer is promoted by the presence of R_2O which has relatively small ion radius.

The present invention sets the ratio of R_2O (in this example, Na_2O) to the total amount of the dielectric layer 24 to 10 wt% or less so that the reduction reaction is suppressed, the generation of the colloidal particles is prevented, and the dielectric layer 24 is made transparent.

3-1-2. Manufacturing Dielectric Layer in Embodiment 2 (Two-Layered Dielectric Layer)

Here, a method of manufacturing the dielectric layer (using a PbO-base glass for the first dielectric layer and a P_2O_5-ZnO-base glass for the second dielectric layer) in Embodiment 2 will be described.

First, a glass paste is prepared by mixing PbO-base glass powder (composed of, for example, 65 wt% of PbO, 10 wt% of B_2O_3, 24 wt% of SiO_2, 1 wt% of CaO, and 2 wt% of Al_2O_3) with an organic binder solution (a solution mixed with 45 wt% of an organic solvent which contains 0.2 wt% of Homogenol as dispersant, 2.5 wt% of dibutyl phthalate as plasticizer, and 10 wt% of ethyl cellulose) at a ratio of 55:45 by weight. The glass paste is applied, with the printing method, to the whole surface of the front panel glass 21 on which the display electrodes 22 and 23 have been formed, to form a coat. The coat

is baked (more specifically, baked for 10 minutes at 500℃) to form the first dielectric layer 241 having thickness of 5 μm.

Note that the first dielectric layer 241 may be formed by sputtering an oxide such as SiO_2, Al_2O_3, and ZnO to form a thin film.

Care should be taken so that the glass material for the first dielectric layer 241 has a higher melting point than the glass material for the second dielectric layer 242.

Secondly, a glass paste is prepared by mixing a P_2O_5-ZnO-base glass powder (composed of, for example, 30 wt% of ZnO, 20 wt% of P_2O_5, 40 wt% of B_2O_3, and 10 wt% of SiO_2) with an organic binder solution (a solution mixed with 45 wt% of an organic solvent which contains 0.2 wt% of Homogenol as dispersant, 2.5 wt% of dibutyl phthalate as plasticizer, and 10 wt% of ethyl cellulose) at a ratio of 55:45 by weight. The glass paste is applied, with the printing method, to the whole surface of the front panel glass 21 on which the first dielectric layer 241 has been formed, to form a coat. The coat is baked (more specifically, baked for 10 minutes at 530℃) to form the second dielectric layer 242 having thickness of 25 μm.

With the above process, the two-layered dielectric layer 24 is formed.

The protection layer 25 approximately 0.9 μm thick made of magnesium oxide (MgO) is formed on the surface of the

dielectric layer 24.

With the above process, the front panel 20 is manufactured.

3.2. Manufacturing Back Panel

A plurality of address electrodes 28 approximately 5 μm thick are formed by applying an Ag-base conductive material on the surface of the back panel glass 27 with the screen printing method in stripes of equal spacing, where the back panel glass 27 is approximately 2.6 μm thick, made of soda lime glass, and formed with the float method.

The dielectric film 29 is then formed by applying the same glass paste as the dielectric layer 24 to the whole surface of the back panel glass 27 on which the address electrodes 28 have been formed, to form a coat having thickness of approximately 20 μm, and baking the coat.

One rib 30 approximately 150 μm high is then formed, using the same glass material as the dielectric film 29, on the dielectric film 29 above each space (approximately 150 μm wide) between each pair of adjacent address electrodes 28. The ribs 30 are formed, for example, by applying repetitively a glass paste containing the above glass material with the screen printing method, then baking the applied glass paste.

After the ribs 30 are formed, the phosphor layers 31 to 33 are formed by applying phosphor inks containing the red (R), green (G), and blue (B) phosphors to the sides of the ribs

30 and the surface of the dielectric film 29 exposed between each pair of adjacent ribs 30, and drying and baking the applied inks.

Here, an example of phosphor materials generally used for PDP will be listed.

red phosphor: $(Y_XGd_{1-X})BO_3: Eu^{3+}$

green phosphor: $Zn_2SiO_4: Mn^{3+}$

blue phosphor: $BaMgAl_{10}O_{17}: Eu^{2+}$

(or $BaMgAl_{14}O_{23}: Eu^{2+}$)

Each phosphor material may be, for example, powder having average grain size of approximately 3 μm. There are several methods for applying the phosphor ink. In this example, the phosphor ink is applied with a method in which the ink is spouted out from a moving nozzle. This method is effective in applying the phosphor ink evenly. It should be noted here that the method for applying the phosphor ink is not limited to the above method, and other methods such as the screen printing method may be used.

With the above process, the back panel 26 is formed.

In the above examples, the front panel glass 21 and the back panel glass 27 are made using soda lime glass. However, they may be made with other materials.

3-3. Completion of PDP

The front panel 20 and the back panel 26 having been

formed as described above are bonded together using a sealing glass. Air in the discharge space 38 is then exhausted until the space becomes high vacuum (8×10^{-7} Torr). The discharge space 38 is then filled with an Ne-Xe-base, He-Ne-Xe-base, or He-Ne-Xe-Ar-base discharge gas with a certain pressure (500-760 Torr).

With this process, the PDP is completed.

4. Manufacturing Examples and Measuring Performance

4-1. Manufacturing Examples and Comparative Examples

To evaluate performance of the PDP of the present invention, PDP examples were manufactured in accordance with the above manufacturing method. 60 variations (No. 1-60) which only differ in the composition of the dielectric layer (ZnO-base glass, P_2O_5-base glass, or ZnO-P_2O_5-base glass) were manufactured. Among these examples No. 1-60, No. 1-54 correspond to the PDP of Embodiment 1 (PDP having a single-layered dielectric layer), and No. 55-60 correspond to the PDP of Embodiment 2 (PDP having a two-layered dielectric layer). Examples No. 4, 20, 29, 43, 47, and 51 do not contain R_2O.

Also, 15 PDPs having a dielectric layer of conventional glass composition (Bi_2O_3-base or PbO-base glass---for detailed composition, see Table 11 and 12) were manufactured as Comparative Examples (No. 61-75). Among these, 3 PDPs (No. 65-67) have a dielectric layer of ZnO-base glass, P_2O_5-base glass, or ZnO-P_2O_5-base glass, each containing more than 10 wt%

of R_2O (Na_2O).

The thickness of the dielectric layer in each of Examples and Comparative Examples No. 1-75 is unified to 30 μm. The dielectric layer in each Example and Comparative Example was formed with the printing method except for No. 58-60 in which the first dielectric layer was formed with the sputtering method.

For each of the manufactured PDPs No. 1-75, dielectric layer discoloring, loss factor ($\tan\delta$), withstand voltage (DC), $\varepsilon \cdot \tan\delta$, permittivity ε, PDP panel brightness (cd/m^2), PDP power consumption (W), etc. were measured. Detailed measuring methods will be shown below. Discoloring of the dielectric layer was observed by naked eye while the PDP was set to the white balance display state.

4-2. Measuring Dielectric Layer Loss Factor ($\tan\delta$) and Permittivity ε

The withstand voltage and loss factor of the dielectric layer of each PDP were measured using an LCR meter (4284A made by Hewlett Packard Company) by applying an alternating voltage (10 kHz of frequency). The detailed measuring method is as follows.

First, 5 adjacent X electrodes in the front panel are connected to be used as shared electrodes. Secondly, 4mm×4mm square Ag electrodes are formed on the dielectric layer. The alternating voltage is then applied to these electrodes while

the capacitance C and the loss factor tanδ are measured. The measured C and tanδ values are displayed on the LCR meter. The permittivity ε value is calculated using the Formula 1 above (d=30μm, S=4mm×4mm).

4-3. Measuring Withstand Voltage of Dielectric Layer

The withstand voltage of the dielectric layer was measured on each of the same dielectric layers as those in the PDPs of Examples and Comparative Examples No. 1-75, each dielectric layer for this measurement being formed on a glass substrate. More specifically, each dielectric layer on a glass substrate was sandwiched by two 4mm×4mm square Ag electrodes in vertical direction, a direct current was applied to between the two Ag electrodes, and the withstand voltage was measured.

The following tables 1-25 show data of each of Examples No. 1-60 and Comparative Examples No. 61-75.

TABLE 1

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)						GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	P_2O_5	ZnO	B_2O_3	SiO_2	MO	R_2O								
1	15	20	40	12	BaO 3	Na_2O 10	550	55	ETHYL CELLULOSE 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.5	550	30	6.4
2	10	25	35	10	MgO 10	K_2O 10	545	65	ACRYLIC 35	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.5	550	30	6.2
3	25	35	30	5	CaO 3	Li_2O 2	540	70	ETHYLENE OXIDE 30	SORBITAN SESQUI-OLEATE 0.1	DIOCTYL PHTHALATE 3.0	545	30	6.3
4	20	30	40	10	—	—	560	35	ETHYL CELLULOSE 65	HOMOGENOL 0.1	DIOCTYL PHTHALATE 3.0	565	30	6.3
5	20	30	30	10	SrO 5	Cs_2O 5	550	40	ETHYL CELLULOSE 60	HOMOGENOL 0.1	GLYCERIN 2.0	553	30	6.5
6	20	30	30	10	CaO 5	K_2O 5	555	50	ACRYLIC 50	GLYCEROL MONO-OLEATE 0.2	DIOCTYL PHTHALATE 1.5	560	30	6.7
7	20	30	30	10	CoO 5	Rb_2O 5	545	65	ACRYLIC 35	HOMOGENOL 0.1	NONE	554	30	6.5
8	20	30	30	10	NiO 5	Ag_2O 5	553	65	ACRYLIC 35	HOMOGENOL 0.1	NONE	559	30	6.5

TABLE 2

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)				GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	P_2O_5	ZnO	Al_2O_3	Na_2O								
9	42	40	13	5	520	55	ETHYL CELLULOSE 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.5	520	20	6.0
10	63	24	9	4	500	65	ACRYLIC 35	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.5	500	15	5.9
11	43	50	7	—	550	70	ETHYLENE OXIDE 30	SORBITAN SESQUI-OLEATE 0.1	DIOCTYL PHTHALATE 3.0	560	20	5.8
12	50	41	7	2	530	35	ETHYL CELLULOSE 65	HOMOGENOL 0.1	DIBUTYL PHTHALATE 3.0	535	15	6.2
13	50	35	14	1	520	40	ETHYL CELLULOSE 60	HOMOGENOL 0.2	GLYCERIN 2.0	525	20	6.5
14	50	39	10	1	515	50	ACRYLIC 50	GLYCEROL MONO-OLEATE 0.2	DIOCTYL PHTHALATE 1.5	519	20	6.1

TABLE 3

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	ZnO	B_2O_3	SiO_2	MO	R_2O								
15	20	55	5	MgO 10	Li_2O 10	535	55	ACRYLIC 45	HOMOGENOL 0.2	DIOCTYL PHTHALATE 2.0	540	30	6.5
16	30	40	12	CaO 10	K_2O 8	540	65	ACRYLIC 35	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 3.0	545	30	6.5
17	35	38	10	BaO 10	Na_2O 7	543	70	ETHYL CELLULOSE 30	SORBITAN SESQUI-OLEATE 0.1	DIBUTYL PHTHALATE 4.0	545	30	6.5
18	44	35	10	SrO 6	Cu_2O 5	540	40	ETHYL CELLULOSE 60	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	545	30	6.5
19	40	45	10	CaO 3	Ag_2O 2	545	45	ETHYL CELLULOSE 55	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	550	30	6.7
20	40	50	10	—	—	558	45	ETHYL CELLULOSE 55	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	560	30	6.8
21	40	40	10	CaO 5	Cs_2O 5	548	50	ETHYL CELLULOSE 50	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	550	30	6.7
22	35	47	8	CaO 5	Rb_2O 5	545	50	ETHYL CELLULOSE 50	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	550	30	6.4

TABLE 4

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)						GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	ZnO	B_2O_3	SiO_2	Al_2O_3	MO	R_2O								
23	27	38	10	5	CaO 10	Ag_2O 10	558	55	ACRYLIC 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	560	30	6.4
24	40	40	5	1	MgO 7	Cu_2O 7	545	65	ACRYLIC 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	550	30	6.4
25	20	55	12	2	SrO 6	Na_2O 5	549	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	555	30	6.3
26	43	40	5	10	BaO 1	K_2O 1	556	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	560	30	6.3
27	40	45	5	5	—	Cs_2O 5	557	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	565	30	6.3
28	40	40	5	5	CaO 5	Rb_2O 5	550	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	560	30	6.3
29	42	43	5	5	CaO 5	—	556	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	560	30	6.3
30	32	47	6	4	CrO 7	Ag_2O 4	550	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	560	30	6.3

TABLE 5

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)						GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	B_2O_3	SiO_2	ZnO	Al_2O_3	Li_2O	MO								
31	20	30	15	20	10	MgO 5	580	55	ACRYLIC 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	595	30	6.7
32	40	10	15	25	3	CaO 7	565	60	ETHYL CELLULOSE 40	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	575	30	6.4
33	35	25	10	20	8	BaO 2	574	60	ETHYL CELLULOSE 40	SORBITAN SESQUI-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	580	30	6.6
34	35	30	10	5	10	SrO 10	560	60	ETHYL CELLULOSE 40	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	570	30	6.5
35	40	25	1	19	5	CaO 10	575	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	585	30	6.5
36	30	20	15	20	5	CaO 10	565	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	575	30	6.5
37	30	15	10	25	8	BaO 12	563	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	575	30	6.7
38	30	15	10	20	10	15	562	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	575	30	6.5

TABLE 6

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (°C)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (°C)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	ZnO	B_2O_3	SiO_2	Al_2O_3	Na_2O								
39	44	35	10.5	5.5	5	540	55	ACRYLIC 45	HOMOGENOL 0.2	DIOCTYL PHTHALATE 2.0	545	20	6.5
40	35	45	10	6	4	549	65	ACRYLIC 35	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 3.0	550	15	6.3
41	50	40	1	5	4	543	70	ETHYL CELLULOSE 30	SORBITAN SESQUI-OLEATE 0.1	DIBUTYL PHTHALATE 4.0	549	15	6.4
42	60	30	5	1	4	542	40	ETHYL CELLULOSE 60	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	548	15	6.5
43	50	30	10	10	—	549	45	ETHYL CELLULOSE 55	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	555	15	6.7
44	50	25	10	10	5	545	45	ETHYL CELLULOSE 55	HOMOGENOL 0.2	DIBUTYL PHTHALATE 4.0	549	20	6.8

TABLE 7

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	ZnO	B_2O_3	SiO_2	Al_2O_3	Ka_2O								
45	60	30	5	1	4	548	55	ACRYLIC 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	550	20	6.5
46	60	30	7	1	2	543	65	ACRYLIC 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	549	20	6.5
47	35	45	10	10	—	549	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	552	20	6.4
48	50	29	10	10	1	545	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	555	20	6.4
49	50	25	12	10	3	550	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	554	20	6.4
50	50	25	10	10	5	548	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	550	20	6.4

TABLE 8

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	Nb_2O_5	ZnO	B_2O_3	SiO_2	Li_2O								
51	19	44	30	7	—	550	55	ACRYLIC 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	555	20	6.8
52	9	60	25	1	5	554	60	ETHYL CELLULOSE 40	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	560	20	6.5
53	14.5	35	38	10.5	2	556	60	ETHYL CELLULOSE 40	SORBITAN SESQUI-OLEATE 0.1	DIBUTYL PHTHALATE 2.0	565	20	6.6
54	15	50	20	10	5	555	60	ETHYL CELLULOSE 40	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	565	20	6.7

TABLE 9

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (°C)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (°C)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	PbO	B_2O_3	SiO_2	CaO	Al_2O_3								
55	50	25	15	10	—	560	55	ETHYL CELLULOSE 45	SORBITAN SESQUI-OLEATE 0.1	DIOCTYL PHTHALATE 2.0	580	5	10.5
56	65	10	22	1	2	550	65	ACRYLIC 40	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	560	5	11.0
57	45	30	20	5	—	570	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	590	5	10.8
58	SiO2 FILM BY SPUTTERING					—	——	——	——	——	—	5	4.0
59	Al2O3 FILM BY SPUTTERING					—	——	——	——	——	—	2	9.0
60	ZnO FILM BY SPUTTERING					—	——	——	——	——	—	2	7.0

TABLE 10

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
55	ZnO 20	B_2O_3 55	SiO_2 5	MgO 10	Li_2O 10	535	55	ACRYLIC 45	HOMOGENOL 0.2	DIOCTYL PHTHALATE 2.0	545	25	6.5
56	P_2O_5 20	ZnO 30	B_2O_3 40	SiO_2 10	–	560	35	ETHYL CELLULOSE 65	HOMOGENOL 0.1	DIBUTYL PHTHALATE 3.0	565	25	6.3
57	ZnO 40	B_2O_3 45	SiO_2 5	Al_2O_3 5	Cs_2O 5	557	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	565	25	6.3
58	ZnO 42	B_2O_3 43	SiO_2 5	Al_2O_3 5	Cs_2O 5	556	65	ETHYL CELLULOSE 35	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	565	25	6.3
59	ZnO 30	B_2O_3 45	SiO_2 5	CaO 10	K_2O 10	540	60	ETHYL CELLULOSE 40	POLYOXYETHYLENE MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	550	28	6.4
60	ZnO 30	B_2O_3 45	SiO_2 5	CaO 10	K_2O 10	540	60	ETHYL CELLULOSE 40	POLYOXYETHYLENE MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	550	28	6.4

TABLE 11

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	Bi_2O_3	ZnO	B_2O_3	SiO_2	CaO								
61*	35	25	26	10	4	580	55	ACRYLIC 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	590	30	12.0
62*	45	30	15	7	3	550	60	ETHYL CELLULOSE 40	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	575	30	12.5
63*	37	28	20	5	10	570	35	ETHYL CELLULOSE 65	SORBITAN SESQUI-OLEATE 0.2	DIOCTYL PHTHALATE 2.0	575	30	11.8
64*	35	30	17	10	8	575	40	ETHYL CELLULOSE 60	SORBITAN SESQUI-OLEATE 0.2	DIOCTYL PHTHALATE 2.0	575	30	11.4
65*	Na_2O 15	20	55	5	5	530	60	ETHYL CELLULOSE 40	SORBITAN SESQUI-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	535	30	6.4
66*	Na_2O 20	30	30	10	10	525	60	ETHYL CELLULOSE 40	SORBITAN SESQUI-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	530	30	6.5
67*	Na_2O 25	35	40	—	—	560	60	ETHYL CELLULOSE 40	SORBITAN SESQUI-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	570	30	6.7

*No. 61～67は比較例

TABLE 12

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (℃)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (℃)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	PbO	B_2O_3	SiO_2	CaO	Al_2O_3								
68*	50	25	15	10	0	560	55	ETHYL CELLULOSE 45	SORBITAN SESQUI-OLEATE 0.2	DIOCTYL PHTHALATE 2.0	580	20	10.5
69*	65	10	22	1	2	550	65	ACRYLIC 40	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	560	20	11.0
70*	45	30	20	5	0	570	70	ETHYL CELLULOSE 30	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	590	20	10.8
71*	55	10	30	5	0	575	35	ETHYL CELLULOSE 65	GLYCEROL MONO-OLEATE 0.2	DIBUTYL PHTHALATE 2.0	590	20	10.7

*No. 68-71 ARE COMPARATIVE EXAMPLES

TABLE 13

EXAMPLE No.	DIELECTRIC LAYER COMPOSITION (wt%)					GLASS SOFTENING POINT (°C)	GLASS POWDER WEIGHT IN GLASS PASTE (%)	WEIGHT OF BINDER CONTAINING SOLVENT (%)	WEIGHT OF DISPERSANT IN BINDER (%)	WEIGHT OF PLASTICIZER IN BINDER (%)	BAKING TEMP. (°C)	DIELECTRIC LAYER THICKNESS (μm)	DIELECTRIC LAYER PERMITTIVITY (ε)
	Bi_2O_3	ZnO	B_2O_3	SiO_2	CaO								
72*	35	25	25	10	5	580	55	ACRYLIC 45	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	590	15	12.0
73*	45	30	15	7	3	550	60	ETHYL CELLULOSE 40	HOMOGENOL 0.2	DIBUTYL PHTHALATE 2.0	575	15	12.5
74*	37	28	20	5	10	570	35	ETHYL CELLULOSE 65	SORBITAN SESQUI-OLEATE 0.2	DIOCTYL PHTHALATE 2.0	575	15	11.8
75*	35	30	17	10	8	575	40	ETHYL CELLULOSE 60	SORBITAN SESQUI-OLEATE 0.2	DIOCTYL PHTHALATE 2.0	575	15	11.4

*No. 72-75 ARE COMPARATIVE EXAMPLES

TABLE 14

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
1	NO DISCOLORING	550	485	0.010	0.064	5.0
2	NO DISCOLORING	552	480	0.008	0.050	5.2
3	NO DISCOLORING	541	472	0.009	0.057	5.3
4	NO DISCOLORING	540	490	0.009	0.057	5.3
5	NO DISCOLORING	542	520	0.011	0.072	5.0
6	NO DISCOLORING	547	450	0.015	0.101	4.6
7	NO DISCOLORING	537	485	0.013	0.085	4.8
8	NO DISCOLORING	540	490	0.014	0.091	4.7

TABLE 15

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
9	NO DISCOLORING	565	491	0.015	0.090	4.5
10	NO DISCOLORING	562	483	0.014	0.083	3.9
11	NO DISCOLORING	551	475	0.009	0.052	4.6
12	NO DISCOLORING	548	507	0.012	0.074	3.8
13	NO DISCOLORING	557	532	0.010	0.065	4.6
14	NO DISCOLORING	558	499	0.009	0.055	4.7

TABLE 16

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
15	NO DISCOLORING	560	498	0.014	0.091	4.7
16	NO DISCOLORING	554	458	0.015	0.098	4.6
17	NO DISCOLORING	545	468	0.015	0.098	4.6
18	NO DISCOLORING	538	495	0.013	0.085	4.7
19	NO DISCOLORING	540	515	0.015	0.101	4.6
20	NO DISCOLORING	552	529	0.017	0.116	4.5
21	NO DISCOLORING	548	513	0.013	0.087	4.8
22	NO DISCOLORING	545	508	0.010	0.064	5.0

TABLE 17

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
23	NO DISCOLORING	520	505	0.012	0.077	4.9
24	NO DISCOLORING	505	500	0.013	0.083	4.8
25	NO DISCOLORING	510	498	0.009	0.057	5.2
26	NO DISCOLORING	522	490	0.010	0.063	5.1
27	NO DISCOLORING	538	485	0.010	0.063	5.1
28	NO DISCOLORING	542	487	0.010	0.063	5.1
29	NO DISCOLORING	526	488	0.010	0.063	5.1
30	NO DISCOLORING	525	489	0.010	0.063	5.1

TABLE 18

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
31	NO DISCOLORING	550	538	0.015	0.101	4.5
32	NO DISCOLORING	554	520	0.011	0.070	5.0
33	NO DISCOLORING	545	531	0.013	0.085	4.8
34	NO DISCOLORING	553	533	0.014	0.092	4.8
35	NO DISCOLORING	532	535	0.014	0.092	4.7
36	NO DISCOLORING	527	525	0.014	0.092	4.7
37	NO DISCOLORING	534	520	0.015	0.101	4.6
38	NO DISCOLORING	550	530	0.013	0.085	4.9

TABLE 19

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
39	NO DISCOLORING	570	532	0.013	0.085	4.4
40	NO DISCOLORING	560	515	0.012	0.076	3.5
41	NO DISCOLORING	555	524	0.014	0.090	3.5
42	NO DISCOLORING	550	532	0.012	0.078	3.6
43	NO DISCOLORING	549	548	0.090	0.060	3.7
44	NO DISCOLORING	560	556	0.013	0.088	4.5

TABLE 20

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR tan δ (10KHz)	ε tan δ	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
45	NO DISCOLORING	533	532	0.011	0.072	4.7
46	NO DISCOLORING	516	532	0.009	0.059	4.8
47	NO DISCOLORING	524	525	0.007	0.045	4.9
48	NO DISCOLORING	532	523	0.008	0.051	4.8
49	NO DISCOLORING	549	522	0.009	0.058	4.7
50	NO DISCOLORING	556	523	0.012	0.077	4.6

TABLE 21

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
51	NO DISCOLORING	562	556	0.007	0.048	4.9
52	NO DISCOLORING	569	532	0.011	0.072	4.7
53	NO DISCOLORING	564	540	0.009	0.059	4.8
54	NO DISCOLORING	568	549	0.013	0.087	4.6

TABLE 22

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
55	NO DISCOLORING	560	520	0.015	0.103	4.5
56	NO DISCOLORING	558	535	0.013	0.090	4.8
57	NO DISCOLORING	550	525	0.013	0.086	4.8
58	NO DISCOLORING	546	485	0.013	0.078	4.8
59	NO DISCOLORING	549	535	0.014	0.100	4.8
60	NO DISCOLORING	549	530	0.013	0.095	4.8

TABLE 23

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR tan δ (10KHz)	ε tan δ	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
61*	YELLOWING	530	830	0.024	0.288	3.0
62*	YELLOWING	545	902	0.025	0.313	2.9
63*	YELLOWING	550	850	0.023	0.271	3.1
64*	YELLOWING	551	832	0.022	0.251	3.2
65*	YELLOWING	530	690	0.102	0.653	3.0
66*	YELLOWING	540	685	0.105	0.683	2.5
67*	YELLOWING	542	680	0.112	0.750	2.1

*No. 61-67 ARE COMPARATIVE EXAMPLES

TABLE 24

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR tan δ (10KHz)	ε tan δ	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
68*	NO DISCOLORING	564	890	0.015	0.158	3.0
69*	NO DISCOLORING	560	900	0.013	0.143	3.1
70*	NO DISCOLORING	550	884	0.013	0.140	3.1
71*	NO DISCOLORING	545	875	0.014	0.150	3.2

*No. 68-71 ARE COMPARATIVE EXAMPLES

TABLE 25

EXAMPLE No.	DIELECTRIC LAYER DISCOLORING	PANEL BRIGHTNESS (cd/m^2)	PANEL POWER CONSUMPTION (W)	LOSS FACTOR $\tan\delta$ (10KHz)	$\varepsilon \tan\delta$	DIELECTRIC LAYER WITHSTAND VOLTAGE (kV)
72*	SLIGHT YELLOWING	543	981	0.024	0.288	2.5
73*	SLIGHT YELLOWING	559	1,023	0.025	0.313	2.4
74*	SLIGHT YELLOWING	560	965	0.023	0.271	2.8
75*	SLIGHT YELLOWING	562	933	0.022	0.251	2.9

*No. 72-75 ARE COMPARATIVE EXAMPLES

5. Performance Evaluation for Examples

5-1. Permittivity ε

It is confirmed from Table 1 that permittivity ε values (ε = 6.2 to 6.7) that are excellent for achieving small power consumption are obtained with the $ZnO-P_2O_5$-base glasses (No. 1-8). The $ZnO-P_2O_5$-base glasses in Examples No. 1-8 are variations having the glass composition of the dielectric layer in Embodiment 1. According to Examples No. 3 and 5-8, to obtain the effects of the present invention, it is desirable that the glass is composed of 10-25 wt% of P_2O_5, 20-35 wt% of ZnO, 30-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 10 wt% or less of DO, and 10 wt% or less of R_2O, where R is Li, Na, K, Rb, Cs, Cu, or Ag, and D is Mg, Ca, Ba, Sr, Co, Cr, or Ni. It should be noted here that it has been confirmed through another experiment that Cu and Cr can be used as DO and R_2O, respectively, in the above definition.

With regard to Example No. 4 that does not include R_2O, it is considered that similar performance will be obtained even if the composition shown in Table 1 is slightly changed in the following ranges: 20-30 wt% of P_2O_5, 30-40 wt% of ZnO, 30-45 wt% of B_2O_3, and 1-10 wt% of SiO_2.

It is confirmed from Table 2 that satisfactory results are obtained from the $ZnO-P_2O_5$-base glasses (No. 9-14) with excellent permittivity ε values (ε = 5.8 to 6.5). According

to Examples No. 9-14, it is desirable that the glass is composed of 42-50 wt% of P_2O_5, 35-50 wt% of ZnO, 7-14 wt% of Al_2O_3, and 5 wt% or less of Na_2O.

It is confirmed from Table 3 that satisfactory results are obtained from the ZnO-base glasses (No. 15-22) with excellent permittivity ε values (ε = 6.4 to 6.8). According to Examples No. 15-22, it is desirable that the glass is composed of 20-44 wt% of ZnO, 38-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 10 wt% or less of R_2O, and 10 wt% or less of MO, where R is Li, Na, K, Rb, Cs, Cu, or Ag, and M is Mg, Ca, Ba, Sr, Co, or Cr. It should be noted here that it has been confirmed through another experiment that Co and Cr can be used as MO in the above definition.

With regard to Example No. 20 that does not include R_2O, it is considered that similar performance will be obtained even if the composition shown in Table 3 is slightly changed in the following ranges: 30-40 wt% of ZnO, 40-60 wt% of B_2O_3, and 1-15 wt% of SiO_2.

It is confirmed from Table 4 that satisfactory results are obtained from the ZnO-base glasses (No. 23-30) with excellent permittivity ε values (ε = 6.3 to 6.4). According to Examples No. 23-30, it is desirable that the glass is composed of 20-43 wt% of ZnO, 38-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 1-10 wt% of Al_2O_3, 10 wt% or less of R_2O, and 10 wt% or less of MO, where R is Li, Na, K, Rb, Cs, Cu, or Ag, and M is

Mg, Ca, Ba, Sr, Co, or Cr. It should be noted here that though not shown in Table 4, it has been confirmed through another experiment that Co can be used as MO in the above definition.

With regard to Example No. 29 that does not include R_2O, it is considered that similar performance will be obtained even if the composition shown in Table 4 is slightly changed in the following ranges: 30-45 wt% of ZnO, 40-55 wt% of B_2O_3, 1-10 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 1-5 wt% of CaO.

It is confirmed from Table 5 that satisfactory results are obtained from the ZnO-base glasses (No. 31-38) with excellent permittivity ε values (ε = 6.4 to 6.7). According to Examples No. 31-38, it is desirable that the glass is composed of 1-15 wt% of ZnO, 20-40 wt% of B_2O_3, 10-30 wt% of SiO_2, 5-25 wt% of Al_2O_3, 3-10 wt% of Li_2O, and 2-15 wt% of MO, where M is Mg, Ca, Ba, Sr, Co, or Cr. It should be noted here that though not shown in Table 5, it has been confirmed through another experiment that each of Co and Cr can be used as MO in the above definition.

It is confirmed from Table 6 that satisfactory results are obtained from the ZnO-base glasses (No. 39-44) with excellent permittivity ε values (ε = 6.3 to 6.8). According to Examples No. 39-44, it is desirable that the glass is composed of 35-60 wt% of ZnO, 25-45 wt% of B_2O_3, 1-10.5 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 5 wt% or less of Na_2O.

With regard to Example No. 43 that does not include

R_2O (in this case, Na_2O), it is considered that similar performance will be obtained even if the composition shown in Table 6 is slightly changed in the following ranges: 40-60 wt% of ZnO, 35-45 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of Al_2O_3.

It is confirmed from Table 7 that satisfactory results are obtained from the ZnO-base glasses (No. 45-50) with excellent permittivity ε values (ε = 6.4 to 6.5). According to Examples No. 45-50, it is desirable that the glass is composed of 35-60 wt% of ZnO, 25-45 wt% of B_2O_3, 1-12 wt% of SiO_2, 1-10 wt% of Al_2O_3, 5 wt% or less of K_2O.

With regard to Example No. 47 that does not include R_2O (in this case, K_2O), it is considered that similar performance will be obtained even if the composition shown in Table 7 is slightly changed in the following ranges: 30-60 wt% of ZnO, 30-50 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of Al_2O_3.

It is confirmed from Table 8 that satisfactory results are obtained from the ZnO-Nb_2O_5-base glasses (No. 51-54) with excellent permittivity ε values (ε = 6.5 to 6.8). According to Examples No. 51-54, it is desirable that the glass is composed of 9-19 wt% of Nb_2O_5, 35-60 wt% of ZnO, 20-38 wt% of B_2O_3, 1-10.5 wt% of SiO_2, and 5 wt% or less of Li_2O.

With regard to Example No. 51 that does not include R_2O (in this case, Li_2O), it is considered that similar

performance will be obtained even if the composition shown in Table 8 is slightly changed in the following ranges: 9-20 wt% of Nb_2O_5, 35-60 wt% of ZnO, 25-40 wt% of B_2O_3, and 1-10 wt% of SiO_2.

As apparent from above, the permittivity ε value in the Examples 1-54 is in a range of 6.0-6.9 or lower, which is as low as approximately half of the permittivity ε value (being in a range of 11.0-12.9) of Comparative Examples 61-64 and 68-75 shown in Tables 11 and 12. As will be described later in detail, the performance of the Comparative Examples 61-67 is inferior to the Examples in terms of the loss factor tanδ or the yellowing.

In Examples No. 55-60 corresponding to the PDP of Embodiment 2 (PDP having a two-layered dielectric layer), the first dielectric layer is made of a PbO-base glass (No. 55-57) or one of a SiO_2-base glass (No. 58), a Al_2O_3-base glass (No. 59), and a ZnO-base glass (No. 60) which are made with the sputtering method, and the second dielectric layer is made of a ZnO-base glass (No. 55 and 57-60) or a P_2O_5-ZnO-base glass (No. 56). As is the case with Examples 1-54, the permittivity ε value in each of the Examples 55-60 is lower than 7.

5-2. Panel Brightness and Panel Power Consumption

It is understood from the results shown in Tables 14-25 that in general, Examples 1-60 consume greatly reduced power compared with Comparative Examples 61-75 while maintaining

almost the same performance as Comparative Examples 61-75 (power consumption of Examples 1-60 is 450-550W while power consumption of Comparative Examples 61-75 is 830-1000W).

With regard to the $\varepsilon \cdot \tan\delta$ value which is proportionate to the power loss w, even the highest value in Examples 1-60, including Examples 4, 20, 29, 43, 47 and 51 that do not contain R_2O in the dielectric layer, does not reach 0.12 while in Comparative Examples 61-75, the value ranges from 0.140 to 0.750. It is understood from this that the PDPs of the Examples consume greatly reduced power and have excellent luminous efficiency. It is also found from the entire measurement results of Examples 1-60 that the composition of the glass for the dielectric layer of the present invention may be determined based on whether the $\varepsilon \cdot \tan\delta$ value is 0.12 or lower or not.

Also, even the highest withstand voltage in Examples 1-60 is approximately 1.5 times the Comparative Examples. It is confirmed from this that Examples 1-60 with the above glass composition have excellent durability.

5-3. Transparency (Discoloring) of Dielectric Layer

It is confirmed from the results shown in Tables 14-22 that no yellowing was observed by naked eye and transparency of the glass is maintained excellently in each of Examples 1-60, while yellowing was observed in Comparative Examples 61-67 and 72-75. It is thought that the transparency contributes to the

excellent panel brightness. Though yellowing was not observed in Comparative Examples 68-71, the permittivity ε value of them is as high as 10.5-11.0, as described earlier.

It is thought that the yellowing occurs to the dielectric layer mainly because, as described earlier, the colloidal particles of Ag and Cu from bus lines reflect visible light. In the dielectric layer of the Examples, the generation of the colloidal particles is suppressed and the transparency is maintained. This is achieved by reducing the amount of R_2O in the glass layer to 10 wt% or less to suppress the reduction reaction of Ag and Cu ions. In other words, it is desirable that the dielectric layer of the present invention contains ZnO (or ZnO and P_2O_5) and 10 wt% or less of R_2O and that the permittivity ε value is 7 or lower. However, the dielectric layer may not necessarily contain R_2O since some Examples (e.g., No. 4, 20) not containing R_2O shows excellent permittivity ε values.

Note that, as the data of Comparative Examples 65-67 shows, the yellowing was observed in the ZnO-base glass or ZnO-P_2O_5-base glass that contains more than 10 wt% of R_2O (e.g., Na_2O). It should be noted here that Comparative Example 67 was manufactured based on the PDP disclosed in Japanese Laid-Open Patent Application No. 8-77930. The yellowing observed in Comparative Examples 65-67 was stronger than the yellowing observed in the other Comparative Examples.

6. Others

In the above embodiments or examples, the present invention is applied to PDPs conforming to the VGA specifications. However, the present invention is not limited to this standard, but can be applied to PDPs conforming to other standards.

The discharge gas used in the PDP of the present invention is not limited to Ne-Xe-base gas. Other discharge gases will provide the same effects.

INDUSTRIAL APPLICABILITY

The above plasma display panel of the present invention is characterized by a small power consumption. The invention is therefore useful in large-screen high-definition TV or the like which consumes relatively a large amount of power conventionally.

Art 19

CLAIMS

1. (Amended) A plasm display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass that contains at least ZnO and 10 wt% or less of R_2O and does not substantially contain PbO and Bi_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag.

2. The plasm display panel of Claim 1, wherein

the permittivity ε of the dielectric layer is 7 or less.

3. The plasm display panel of Claim 1, wherein

the dielectric layer contains 10-25 wt% of P_2O_5, 20-35 wt% of ZnO, 30-40 wt% of B_2O_3, 5-12 wt% of SiO_2, 10 wt% or less of R_2O, and 10 wt% or less of DO, and the permittivity ε of the dielectric layer is 7 or less, wherein D is selected from a

group consisting of Mg, Ca, Ba, Sr, Co, Cr, and Ni.

4. The plasm display panel of Claim 1, wherein

the dielectric layer is composed of a $ZnO-P_2O_5$-base glass which contains 42-50 wt% of P_2O_5, 35-50 wt% of ZnO, 7-14 wt% of Al_2O_3, and 5 wt% or less of Na_2O, and the permittivity ε of the dielectric layer is 7 or less.

5. The plasm display panel of Claim 1, wherein

the dielectric layer is composed of a ZnO-base glass which contains 20-44 wt% of ZnO, 38-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 10 wt% or less of R_2O, and 10 wt% or less of MO, and the permittivity ε of the dielectric layer is 7 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag, and M is selected from a group consisting of Mg, Ca, Ba, Sr, Co, and Cr.

6. The plasm display panel of Claim 1, wherein

the dielectric layer is composed of a ZnO-base glass which contains 20-43 wt% of ZnO, 38-55 wt% of B_2O_3, 5-12 wt% of SiO_2, 1-10 wt% of Al_2O_3, 10 wt% or less of R_2O, and 10 wt% or less of MO, and the permittivity ε of the dielectric layer is 7 or less, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag, and M is selected from a group consisting of Mg, Ca, Ba, Sr, Co, and Cr.

7. The plasm display panel of Claim 1, wherein

the dielectric layer is composed of a ZnO-base glass which contains 1-15 wt% of ZnO, 20-40 wt% of B_2O_3, 10-30 wt% of SiO_2, 5-25 wt% of Al_2O_3, 3-10 wt% of Li_2O, and 2-15 wt% of MO, and the permittivity ε of the dielectric layer is 7 or less, wherein M is selected from a group consisting of Mg, Ca, Ba, Sr, Co, and Cr.

8. The plasm display panel of Claim 1, wherein

the dielectric layer is composed of a ZnO-base glass which contains 35-60 wt% of ZnO, 25-45 wt% of B_2O_3, 1-10.5 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 5 wt% or less of Na_2O, and the permittivity ε of the dielectric layer is 7 or less.

9. The plasm display panel of Claim 1, wherein

the dielectric layer is composed of a ZnO-base glass which contains 35-60 wt% of ZnO, 25-45 wt% of B_2O_3, 1-12 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 5 wt% or less of K_2O, and the permittivity ε of the dielectric layer is 7 or less.

10. The plasma display panel of Claim 1, wherein

the dielectric layer is composed of a ZnO-Nb_2O_5-base glass which contains 9-19 wt% of Nb_2O_5, 35-60 wt% of ZnO, 20-38 wt% of B_2O_3, 1-10.5 wt% of SiO_2, and 5 wt% or less of Li_2O, and permittivity ε of the dielectric layer is 7 or less.

11. (Amended) A plasm display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 20-30 wt% of P_2O_5, 30-40 wt% of ZnO, 30-45 wt% of B_2O_3, and 1-10 wt% of SiO_2 and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

12. (Amended) A plasm display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 30-45 wt% of ZnO, 40-60 wt% of B_2O_3, and 1-15 wt% of SiO_2 and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

13. (Amended) A plasm display panel in which a space between a

first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 30-45 wt% of ZnO, 40-55 wt% of B_2O_3, 1-10 wt% of SiO_2, 1-10 wt% of Al_2O_3, and 1-5 wt% of CaO, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

14. (Amended) A plasm display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 40-60 wt% of ZnO, 35-45 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of Al_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

15. (Amended) A plasm display panel in which a space between a

first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 30-60 wt% of ZnO, 30-50 wt% of B_2O_3, 1-10 wt% of SiO_2, and 1-10 wt% of Al_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

16. (Amended) A plasm display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is made of a glass which is composed of 9-20 wt% of Nb_2O_5, 35-60 wt% of ZnO, 25-40 wt% of B_2O_3, and 1-10 wt% of SiO_2, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less.

17. (Amended) A plasm display panel in which a space between a first plate and a second plate facing each other is filled with

a discharge gas, a plurality of pairs of display electrodes made of Ag are formed on a surface of the first plate facing the second plate, and the surface of the first plate is covered with a dielectric layer covering the plurality of pairs of display electrodes, characterized in that:

the dielectric layer is composed of

a first dielectric layer which either is a thin film of SiO_2, Al_2O_3 or ZnO or is made of a glass containing at least PbO or Bi_2O_3 and covers the plurality of pairs of display electrodes, and

a second dielectric layer made of a glass in which a product of permittivity ε and loss factor $\tan\delta$ is 0.12 or less, the second dielectric layer covering the first dielectric layer.

18. The plasm display panel of Claim 17, wherein

the second dielectric layer contains is made of a glass that at least ZnO and 10 wt% or less of R_2O and does not contain PbO and Bi_2O_3, wherein R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag.

19. The plasm display panel of Claim 17, wherein

a total thickness of the dielectric layer is 40 μm or less, and a thickness of the first dielectric layer is half of the total thickness or less.

ABSTRACT

The present invention provides a plasma display panel in which a space between a first plate and a second plate facing each other is filled with a discharge gas, a plurality of pairs of display electrodes made of Ag or Cu are formed on a surface of the first plate facing the second plate, and the surface is covered with a dielectric layer covering the display electrodes, where the dielectric layer is made of a glass that contains at least ZnO and 10 wt% or less of R_2O and does not substantially contain PbO and Bi_2O_3, and a product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is 0.12 or less, where R is selected from a group consisting of Li, Na, K, Rb, Cs, Cu, and Ag. The plasma display panel effectively prevents display performance from deteriorating by suppressing deposition of colloidal particles of Ag and Cu out of the display electrodes into the dielectric layer. The plasma display panel consumes a small amount of power since the product of permittivity ε and loss factor $\tan\delta$ of the dielectric layer is lower than conventional ones. Also, the manufacturing cost of the plasma display panel is reduced due to reduction in the cost for baking the dielectric layer or the like which is achieved since the softening point of the glass with the above composition is 600℃ or less, lower than conventional ones.

09927 "60902760

FIG. 1



09/720609

FIG. 2



09/720609

09/720609

FIG. 3



09/720609

Docket No.
NAK1-BN46

Declaration and Power of Attorney For Patent Application

English Language Declaration

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

PLASMA DISPLAY PANEL AND METHOD FOE PRODUCING THE PLASMA DISPLAY PANEL

the specification of which

(check one)

☐ is attached hereto.

☒ was filed on April 26,2000 as United States Application No. or PCT International Application Number PCT/JP00/02715

and was amended on _____
(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)			Priority Not Claimed
H11-122107	JAPAN	28/April/1999	☐
(Number)	(Country)	(Day/Month/Year Filed)	
H11-304431	JAPAN	26/October/1999	☐
(Number)	(Country)	(Day/Month/Year Filed)	
			☐
(Number)	(Country)	(Day/Month/Year Filed)	

I hereby claim the benefit under 35 U.S.C. Section 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)	(Filing Date)
(Application Serial No.)	(Filing Date)
(Application Serial No.)	(Filing Date)

I hereby claim the benefit under 35 U. S. C. Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. Section 112, I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, C. F. R., Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. *(list name and registration number)*

4 **Joseph W. Price, Reg. No. 25,124**
Albin H. Gess, Reg. No. 25,726
Franklin D. Ubell, Reg. No. 27,009
Doyle B. Johnson, Reg. No. 39,240
Michael J. Moffatt, Reg. No. 39,304
Bradley D. Blanche, Reg. No. 38,387

Send Correspondence to: **Joseph W. Price**
PRICE, GESS & UBELL
2100 S.E. Main St., Ste. 250
Irvine, CA 92614

Direct Telephone Calls to: *(name and telephone number)*
Joseph W. Price, 949/261-8433

Full name of sole or first inventor 1-∞ Masaki AOKI
Sole or first inventor's signature Masaki Aoki Date December 12, 2000
Residence 5-12-1, Aoshinke Minoo-shi, Osaka-fu 562-0024 Japan JPx
Citizenship Japan
Post Office Address same as residence

Full name of second inventor, if any 2-∞ Katsuyoshi YAMASHITA
Second inventor's signature Katsuyoshi Yamashita Date December 12, 2000
Residence 5-7-206, Myoukenzaka, Katano-shi, Osaka-fu, 576-0021, Japan JPx
Citizenship Japan
Post Office Address same as residence

over

Full name of third inventor, if any
3 - oo Mitsuhiro OHTANI
Third inventor's signature — Mitsuhiro Ohtani — Date: December 12, 2000
Residence
3-8-31, Kouryounakamachi, Sakai-shi, Osaka-fu, 590-0024, Japan JPX
Citizenship
Japan
Post Office Address
same as residence

Full name of fourth inventor, if any
4 - oo Junichi HIBINO
Fourth inventor's signature — Junichi Hibino — Date: December 12, 2000
Residence
919-1-A712, Utiage, Neyagawa-shi, Osaka-fu, 572-0802, Japan JPX
Citizenship
Japan
Post Office Address
same as residence

Full name of fifth inventor, if any
Fifth inventor's signature — Date
Residence
Citizenship
Post Office Address

Full name of sixth inventor, if any
Sixth inventor's signature — Date
Residence
Citizenship
Post Office Address

09/736,659